BERLIN CO., LTD.
Since 1962
ISO-9001
ISO-14001
ISO-45001
CSR-GRIG4 AA1000
National Quality Award
National Award of Small and Medium Business
Testing Laboratory 2544

ACRYLIC SOLVENT BASE MASONRY PAINT

PRODUCT CODE:

- BP1551

DESCRIPTION

- A acrylic resin based paint with alkali-resistance pigments and additives.

CHARACTERISTICS

- Tough film with good adhesion properey.
- Quick drying and easy application.
- Good resistance to water and alkali.
- Good weather ability and gloss retention.

USAGE

- As a protection paint for inner and outer wall of architecture.

BASIC DATA

- FACKING: 1Pack.
- COLOR: White, light and others colors.
- HIDING POWER: White 12.5M^2/L; yellow, red, blue, green 8M^2/L; others 12.5M^2/L MIN.
- GLOSS: Glossy, semi-gloss, flat, matte.
- SP.GR: approx 1.0 (depend on different color and gloss).
- VISCOSITY : 75~95 KU (25℃).
- DRYING TIME (25℃): Tack-free: 30 min; hard-dry: 2 hrs.
- SOLID (%VOL): 37±3% (depend on different color and gloss).
- COVERAGE (THEOR.): 40M^2/Gal @35μm.
- SUITABLE: PRIMER: Solvent base masonry primer etc.
- SHELF LIFE: In normal condition, one year, at least.

APPLICATION INSTRUCTION

- SURFACE TREATMENT: Surface must be clean, dry and remove foreign.
- THINNER: SV-7700.
- APPLICATION: Brush, roll, air spray, and airless spray.
- RECOMMENDED DFT.: 30-40 μm (per coat).
- COATING INTERVAL: 3 hrs.

REMARKS

- Stir thoroughly, thinner may be used to reduce viscosity.
- Remove all foreign particles, oils, grease and moistures from the surface before application.
- Don't apply when the temperature is below 10℃, over 40℃, moisture is over 85% or the surface temperature of substrate is not higher than the dew point for at least 3℃.
- Keep away from heat, sparks and flame.
- Stored with good ventilation.

- Keep adequate ventilation during application.
- Lid must be sealed to avoid vaporizing & skinning.
- Before application it is necessary to get a curing time about 21 days and the surface moisture must be under 10% for new concrete.
- The actual coverage may vary, depending on application technique, job conditions and type of surface. Under brushing & rolling application the actual coverage is estimated at 70% & 60% for spraying of the theoretical coverage.
- When exceeding the specified overcoat duration, the to-be painted surface must be prepared by proper surface treatment to ensure adequate adhesion between coatings.

NOTICE

- The parts of data base above could be affect by application condition at job site, please reference guide specification or contact with relative technical personnel.
- The basic date may vary from color or gloss.
- Revision Date:2024.04.15

Headquarter：
No.43,TA-Yeh South Road,Kaohsiung
TEL：(07)871-1101 FAX：(07)871-6583

Office：
No.9, Aly. 8, Ln. 811, Sec. 4, Zhongqing Rd., Daya Dist., Taichung City
TEL：(04)2560-3616 FAX：(04)2560-3697

Branch Office：
6F,No.168,Yung Chi Road,Taipei
TEL：(02)2768-7216 FAX：(02)2756-0374

email：info@berlin.com.tw